

09/27/00



JCS665 U.S. PTO

LAW OFFICES
SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC

2100 PENNSYLVANIA AVENUE, N.W.
 WASHINGTON, D.C. 20037-3202
 TELEPHONE (202) 293-7060
 FACSIMILE (202) 293-7860

JCS631 U.S. PTO
 09/27/00
 09/27/00

CALIFORNIA OFFICE

1010 EL CAMINO REAL
 MENLO PARK, CA 94025
 TELEPHONE (650) 325-5800
 FACSIMILE (650) 325-6606

BOX: PATENT APPLICATION

Assistant Commissioner for Patents
 Washington, D.C. 20231

September 27, 2000

JAPAN OFFICE

TOEI NISHI SHIMBASHI BLDG. 4F
 13-5 NISHI SHIMBASHI 1-CHOME
 MINATO-KU, TOKYO 105, JAPAN
 TELEPHONE (03) 3503-3760
 FACSIMILE (03) 3503-3756

Re: **Application of Masakazu NISHIKAWA and Makoto NAGAO**
FLOPPY DISK
 Our Reference: Q58116

Dear Sir:

Attached hereto is the application identified above including the specification, claims, executed Declaration and Power of Attorney, one (1) priority document, executed Assignment and PTO Form 1595.

The Government filing fee is calculated as follows:

Total Claims	20 - 20 =	0 x \$18 =	\$ 000.00
Independent Claims	2 - 3 =	0 x \$78 =	\$ 000.00
Base Filing Fee	(\$690.00)		\$ 690.00
Multiple Dep. Claim Fee	(\$260.00)		\$ 000.00
TOTAL FILING FEE			\$ 690.00
Recordation of Assignment Fee			\$ 40.00
TOTAL U.S. GOVERNMENT FEE			\$ 730.00

Checks for the statutory filing fee of \$ 690.00 and Assignment recordation fee of \$ 40.00 are attached. You are also directed and authorized to charge or credit any difference or overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. 1.16 and 1.17 and any petitions for extension of time under 37 C.F.R. 1.136 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

Priority is claimed from:

Japanese Patent Application

11-272644

Filing Date

September 27, 1999

Respectfully submitted,
 SUGHRUE, MION, ZINN, MACPEAK & SEAS
 Attorneys for Applicant(s)

By John Callahan Reg. No. 32,607
 Mark Boland
 Registration No. 32,197

MXB:slb

TITLE OF THE INVENTION

FLOPPY DISK

BACKGROUND OF THE INVENTION

5 The present invention relates to a magnetic recording medium with high recording density, and in particular, to a removable type magnetic recording medium to be used in auxiliary memory unit, image storage unit, etc. of a computer. Further, the invention relates to a floppy disk
10 using a flexible support member with high recording density of 1 GB or more per square inch.

 With extreme increase in the capacity of electronic data prepared in devices such as personal computer, there are now strong demands on the development of a removable
15 type disk comprising high capacity magnetic recording medium for the purpose of storing large amount of electronic data and for backup operation.

 Up to now, digital video tape has been primarily used as ultra-high density recording medium for business use.
20 With rapid increase in the amount of information in recent years, there are now demands on technical development to seek higher capacity and higher speed for recording and reproduction. Instead of the video tape currently used as main stream in this field, attempts are now being made to
25 use removable type disk with better recording and reproducing speed as a digital recording medium for business use.

 On the other hand, in the high density magnetic

recording medium of GB class currently in use, a disk made of aluminum, glass, etc., i.e. the so-called hard disk, is used. When shock is applied on the device, head crash may occur, and both medium and head may be subjected to serious damage. This problem of shock-resistant property is not yet overcome in the removable type hard disk, and this has hindered the use as recording means in portable devices such as digital disk camera.

When the support member is changed from hard disk to a flexible member of the same type as a floppy disk, it is advantageous in that the recording unit can be produced in lightweight design, and damage at head crash can be alleviated. In this respect, there are now strong demands on the development of high density removable type magnetic recording medium using a flexible support member with high shock-resistant property as substrate.

In a removable type magnetic recording medium, a magnetic layer comprising a ferromagnetic metal or alloy is formed on a substrate. In particular, in the high density magnetic recording medium, for a ferromagnetic layer formed on the magnetic recording medium, a magnetic layer is formed by vacuum film forming method.

However, in the removable type magnetic recording medium using a flexible support member, there have been problems in that cracking occurs during manufacturing process and the product cannot be used as a medium.

It is an object of the present invention to provide a floppy disk type magnetic recording medium with high

quality in a removable type high density magnetic recording medium using a flexible support member as substrate, and to prevent cracking in the manufacturing process.

5

SUMMARY OF THE INVENTION

The above problems can be solved by a floppy disk, which comprises a primer layer, a magnetic layer, a protective layer, and a lubricating layer coated on at least one of the surfaces of a flexible nonmagnetic support member, whereby a seed layer is provided between the flexible support member and the primer layer.

Also, the present invention provides a floppy disk as described above, wherein there is provided a flattening layer, comprising a heat-resistant polymer on the flexible nonmagnetic support member.

Further, the present invention provides a floppy disk as described above, wherein thickness of the flexible support member is within the range of 30 - 100 μ m.

Also, the present invention provides a floppy disk as described above, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

Further, the present invention provides a floppy disk as described above, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

Also, the present invention provides a floppy disk, which comprises a flattening layer with thickness of 0.1 -

5 μm , a seed layer, a nonmagnetic primer layer containing
Cr alloy with Cr concentration of 77 - 100 atom %, a
magnetic layer containing Co-Cr alloy with Cr concentration
of 10 - 30 atom %, a protective layer, and a lubricating
5 layer, all of said layers being coated on at least one of
the surfaces of a flexible support member with thickness of
30 - 100 μm , whereby thickness of the seed layer is 5 -
100 nm, and linear expansion coefficient (E_{SE}) of the metal
seed layer and linear expansion coefficient (E_{UL}) of the
10 nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|$
 $|E_{UL}| < 0.3$, and tensile strength (S_{SE}) of the metal seed
layer and tensile strength (S_{UL}) of the nonmagnetic primer
layer satisfy the relation: $S_{SE}/S_{UL} > 1$.

15 DESCRIPTION OF THE PREFERRED EMBODIMENT

The present inventors have found that it is possible
to provide a floppy disk with stable performance
characteristics. Specifically, on at least one of the
surfaces of a flexible nonmagnetic support member, a primer
20 layer, a magnetic layer, a protective layer, and a
lubricating layer are coated to obtain a floppy disk. By
providing a seed layer between the flexible support member
and the primer layer, it is possible to prevent cracking in
the manufacturing process and to obtain a floppy disk with
25 stable performance characteristics.

Further, a specific type of flattening layer, a primer
layer and a magnetic layer are formed on the nonmagnetic
support member. Also, the following material is used as

seed layer, i.e. linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. As a result, it was found that cracking can be prevented when the medium is prepared.

Specifically, cracking often occurs on the ferromagnetic metal thin film formed on a substrate using a flexible material as the nonmagnetic support member. It was found that this is caused by flatness which is required on a magnetic recording medium with high recording density and also by thermal expansion of the seed layer, the primer layer, etc. formed on the magnetic recording medium.

When a hard disk made of aluminum, glass, etc. is used as a support member, it is possible to attain flatness closer to mirror surface by polishing. In case of a floppy disk, however, a flexible support member is used as the support member, and it is very difficult to improve the flatness by polishing. In this respect, by providing a flattening layer made of polymer on the flexible support member, the surface property similar to a hard disk support member can be attained. On the flattening layer, a nonmagnetic primer layer and a magnetic layer are formed by sputtering. In order to increase magnetostatic property and electromagnetic transfer characteristics of the magnetic layer, it is necessary to heat the support member

at high temperature of 100°C - 300°C. Or, temperature of the support member is effectively increased when bias voltage application, RF sputtering method, etc. are used.

5 The medium with the nonmagnetic primer layer and the magnetic layer formed on it is cooled down to room temperature and is taken out of a sputtering device. During the manufacturing process with varying temperature, the flexible support member, the flattening layer, the nonmagnetic primer layer, and the magnetic layer are
10 subject to thermal expansion and shrinking.

In a hard disk, the support member is made of hard material, and metal, ceramics, glass, etc. are used as the material. In this respect, difference of expansion coefficient is small between the primer layer and the
15 support member, and there is less possibility that cracking occurs during heating and cooling processes due to the difference in thermal expansion. In a magnetic recording medium using a flexible support member as substrate, the flexible support member and the flattening layer are made
20 of macromolecular compositions, and the nonmagnetic primer layer and the magnetic layer are made of metal material. For this reason, thermal expansion or shrinking differs between these two layers by about one digit. The material of the nonmagnetic primer layer cannot endure the
25 deformation of the support member when cooled down, and this may result in cracking on the magnetic recording medium.

When a nonmagnetic primer layer, i.e. a seed layer, is

provided between the flattening layer and the primer layer, a force generated between the flattening layer and the primer layer which occurs when the support member is cooled down is received by the primer layer and the seed layer.

- 5 As a result, film strength is improved, and cracking can be prevented.

- It is proposed to use the following material as the material of the seed layer and the primer layer, i.e. a material, in which linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. Then, it is possible to cope with the force, which is generated due to the difference of linear expansion coefficient between the primer layer and the magnetic layer in the cooling process, and cracking can be prevented on higher level.
- 10
- 15

- Specifically, the invention provides a floppy disk with ultra-high recording density, which comprises at least a primer layer, a magnetic layer, a protective layer, and a lubricating layer on a flexible support member, and by which it is possible to prevent cracking during the preparation of the medium.
- 20

- For the purpose of preventing cracking during the above process, such materials are used that linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic
- 25

primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$,
and tensile strength (S_{SE}) of the metal seed layer and
tensile strength (S_{UL}) of the nonmagnetic primer layer
satisfy the relation: $S_{SE}/S_{UL} > 1$. As a result, it is
5 possible to prevent cracking during the preparation of the
medium and to provide a floppy disk with high recording
density.

Next, description will be given on the materials which
are preferably used in the present invention.

10 As the support member of the magnetic recording medium
of the present invention, polyethylene terephthalate,
polyethylene naphthalate, polyimide, polyamide,
polyamideimide, polybenzoxazole, etc. may be used. Young's
modulus of the support member of the magnetic recording
15 medium of the present invention is preferably 200 - 1600
kg/mm², or more preferably 300 - 800 kg/mm². The thickness
of the support member is preferably 20 - 150 μ m, or more
preferably 30 - 80 μ m.

To improve the flatness of the surface of the support
20 member, a flattening layer is provided on the support
member. For the flattening layer, heat-resistant polymer
may be extensively used. More preferably, the material
such as silicone resin, polyamide resin, polyamideimide
resin, polyimide resin, etc. may be used. These materials
25 have high heat-resistant property and exhibit excellent
performance in surface property and magnetostatic property.
Coating thickness of the flattening layer is preferably 0.1
- 5.0 μ m, or more preferably 0.5 - 3.0 μ m, or most

preferably 0.8 - 2.0 μm .

Micro-size projections, e.g. fine particles of inorganic substances such as SiO_2 , Al_2O_3 , TiO_2 , etc. or fine particles of organic substances, may be provided on the surface of the flattening layer. Particle size of the fine particles to be used for the formation of micro-size projections is preferably 5 - 40 nm, or more preferably 10 - 35 nm, or most preferably 15 - 30 nm. The height of the projection to be formed on the surface of the flattening layer is preferably 30 nm or less.

When particle size of the fine particles to be formed on the surface of the flattening layer is less than 5 nm, the effect of the presence of fine particles on the surface of the flattening layer cannot be attained. If it is more than 40 nm, surface irregularities may occur on the layer subsequently formed, and this may lead to lower flatness.

The seed layer to be formed between the flattening layer and the primer layer, preferably contains at least one type of metal of Ta, Mo, W, V, Zr, Cr, Rh, Hf, Nb, Mn, Ni, Al, Ru, Ti and Si, or an alloy containing two types or more of these elements. Also, the material may contain oxygen, nitrogen, etc.

The thickness of the seed layer is preferably 10 - 100 nm, or more preferably 15 - 80 nm, or most preferably 20 - 60 nm. If the seed layer is thinner than 10 nm, the structure of the seed layer may become discontinuous. A force generated due to thermal shrinking may be applied on the primer layer, and cracking may occur. If it is thicker

than 100 nm, cracking and film detachment may occur on the magnetic recording medium due to film stress on the seed layer. The seed layer can be produced by DC sputtering under argon atmosphere. The temperature suitable for
5 producing the seed layer is 5°C - 250°C, or more preferably 10°C - 200°C.

As the material for the nonmagnetic primer layer, it is preferable to use chromium or an alloy containing chromium and at least one type of metals of Ti, W, Mo, V,
10 Ta, B, Si, Nb, Zr, Al and Mn. Cr concentration of the nonmagnetic primer layer is 77 - 100 atom %, or more preferably 80 - 95 atom %, and the remainder is metals of the other elements.

The thickness of the nonmagnetic primer layer is
15 preferably 5 - 500 nm, or more preferably 10 - 100 nm. If the primer layer is thicker than 500 nm, particle size of the magnetic layer is increased, and this leads to the increase of medium noise.

It is necessary to design in such manner that linear
20 expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|E_{UL} < 0.3$, and tensile strength (S_{SE}) of the seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the
25 relation: $S_{SE}/S_{UL} > 1$. More preferably, the following relations must be satisfied:

$$|E_{SE} - E_{UL}|E_{UL} < 0.2 \text{ and}$$

$$S_{SE}/S_{UL} > 1.1$$

As the material for the medium to satisfy the above relations, Ta (film thickness: 20 nm; input power: 11.4 W/cm²; argon partial pressure: 8 mTorr) may be used as the material for the seed layer, and CrTi₂₀ (film thickness: 60 nm; input power 11.4 W/cm²; argon partial pressure: 15 mTorr) may be used as the material for the nonmagnetic primer layer.

As the magnetic material to form the magnetic layer, cobalt-chromium alloy may be preferably used. In particular, it is preferable to use cobalt-chromium alloy containing Pt, Ta, Ni, Si, B, Ni, or Pd. Also, oxygen may be contained.

Among these materials, it is more preferable to use Co-Cr-Pt or Co-Cr-Pt-Ta because these have superb property in both output and noise characteristics. In addition to cobalt-chromium alloy, barium ferrite may be used. Cr concentration in the ferromagnetic layer is preferably 10 - 30 atom %, or more preferably 12 - 28 atom %, or most preferably 15 - 25 atom %. Film thickness of the magnetic layer is preferably 10 - 300 nm, or more preferably 10 - 60 nm.

It is preferable that the nonmagnetic primer layer and the magnetic layer are formed by vacuum film forming method. In particular, it is preferable to use the sputtering method because film can be formed without changing composition of the elements. Also, it is preferable to continuously form the film under vacuum condition for all of the seed layer, the primer layer and the magnetic layer.

It is preferable to provide a carbon film comprising amorphous carbon, graphite, diamond structure or mixture of these materials prepared by plasma CVD method, sputtering method, etc. on the magnetic layer as a protective layer.

- 5 In particular, it is preferable to use hard amorphous carbon film, generally called diamond-like carbon. This hard carbon film is preferably 1000 kg/mm^2 or more in Vickers hardness, or more preferably 2000 kg/mm^2 .

- The film thickness of the protective layer is
10 preferably $2.5 - 30 \text{ nm}$, or more preferably $5 - 25 \text{ nm}$.

- In the magnetic recording medium of the present invention, with the purpose of improving running durability and corrosion-resistant property, it is preferable to add lubricant or rust-preventive agent on the magnetic layer or
15 the protective layer.

- As the lubricant, hydrocarbon type lubricant, fluorine type lubricant, extreme-pressure additive, etc. already known in the art may be used. As the hydrocarbon type lubricant, carboxylic acids such as stearic acid, oleic
20 acid, etc., esters such as butyl stearate, sulfonic acids such as octadecyl sulfonic acid, phosphoric acid esters such as monooctadecyl phosphate, alcohols such as stearyl alcohol, oleyl alcohol, etc., carboxylic acid amide such as stearic acid amide, etc., amines such as stearyl amine may
25 be used.

As the fluorine type lubricant, a lubricant prepared by substituting a part or all of the alkyl groups in the hydrocarbon type lubricant by fluoroalkyl group or

perfluoropolyether group may be used. As the perfluoro-
polyether group, perfluoromethylene oxide polymer,
perfluoroethylene oxide polymer, perfluoro-n-propylene
oxide polymer $(CF_2CF_2CF_2O)_n$, perfluoroisopropylene oxide
5 polymer $(CF(CF_3)CF_2O)_n$ or copolymer of these compounds may
be used.

As the extreme-pressure additive, phosphoric acid
esters such as trilauryl phosphate, phosphorous acid esters
such as trilauryl phosphite, thiophosphorous acid esters
10 such as trilauryl trithiophosphite, sulfur type extreme-
pressure agent such as dibenzyl disulfide may be used.

The lubricants as described above may be used alone or
in combination. To apply these lubricants on the
protective layer, the lubricant is dissolved in an organic
15 solvent, and it is coated by wire bar method, gravure
method, spin coat method, dip coat method, etc., or it may
be attached by vacuum evaporation method.

The coating quantity of the lubricant is preferably 1
- 30 mg/m^2 , or more preferably, 2 - 20 mg/m^2 .

20 As the rust-preventive agent to be used in the present
invention, nitrogen-containing heterocyclic compounds such
as benzotriazole, benzimidazole, purine, pyrimidine, etc.,
derivatives prepared by introducing alkyl side-chain to or
the base nucleus, nitrogen- or sulfur-containing hetero-
25 cyclic compounds and derivatives such as benzothiazole, 2-
mercaptobenzothiazole, tetrazaindene cyclic compound,
thiouracil compound may be used

[Embodiments]

In the following, description will be given on concrete examples of the present invention:

(Example 1)

On a polyimide flexible support member of 75 μm in thickness, polyimide resin of 1 μm in thickness was provided as a flattening layer. Tantalum was coated on it in thickness of 20 nm as a seed layer by DC sputtering method under the conditions of argon partial pressure of 8 mTorr, input power of 11.4 W/cm², and support member temperature of 20°C. Further, as the nonmagnetic primer layer, chromium alloy containing titanium by 20 atom % was coated in thickness of 60 nm by DC sputtering method under the conditions of argon partial pressure of 15 mTorr, input power of 11.4 W/cm², and support member temperature of 200°C.

Next, as the magnetic layer, a Co alloy thin film containing Cr by 20 atom % and Pt by 12 atom % was formed by DC sputtering method on the nonmagnetic primer layer under the conditions of argon partial pressure of 1.5 mTorr, input power of 11.4 W/cm², support member temperature of 200°C, and film thickness of 30 nm.

Next, on the magnetic layer, a carbon protective layer of 20 nm in thickness was formed by DC sputtering method under the conditions of argon partial pressure of 3 mTorr, and input power of 5.71 W/cm².

Further, monolauryl phosphate ($\text{CH}_3(\text{CH}_2)_{11}\text{OPO}_3\text{H}_2$) and amine stearate ($\text{CH}_3(\text{CH}_2)_{17}\text{NH}_2$) were dissolved in methanol, and this solution was coated as lubricant by wire bar

method in such manner that molar ratio of organic acid and amine will be 1:1 and coating amount of these two substances will be 6 mg/m², and a floppy disk was prepared. (Examples 2 to 6)

- 5 A floppy disk was prepared for each of Examples 2 to 12 by the same procedure as in Example 1 except that the material for the seed layer or the material for the nonmagnetic primer layer in Example 1 was changed to the material shown in Table 1.

10 (Comparative example 1)

A floppy disk of Comparative example 1 was prepared by the same procedure as in Example 1 except that the seed layer was not provided.

(Comparative examples 2 to 11)

- 15 A floppy disk for each of Comparative examples 2 to 11 was prepared by the same procedure as in Example 1 except that the material for the seed layer in Example 1 was changed to the material shown in Table 1.

- Each magnetic recording medium in the Examples and
20 Comparative examples as described above was measured by the measuring methods given below. The results of the measurement are shown in Table 1.

(Measuring methods)

(1) Linear expansion coefficient

- 25 For the measurement of linear expansion coefficient, a sputtering device (S-50S; Shibaura Engineering Works Co., Ltd.) was used. The specimen was heated to 300°C using a lamp heater under vacuum condition of 10⁻⁶ Torr or lower.

The amount of deformation of the specimen was obtained using a strain gauge (strain gauge WK; Micromasurement Inc.) mounted on both surfaces of the specimen.

5 A specimen of 5 mm × 30 mm with a single layer formed on each of both surfaces of a polyimide support member was used. To exclude the influence of deformation of the support member, the strain gauge was also mounted on the support member using polyimide only, and the amount of deformation was measured on each of the specimens.

10 The amount of deformation (V_{sp}) of the specimen with the film formed on it and the amount of deformation (V_{pi}) of the support member using polyimide only were measured. A difference of the amount of deformation between these two, i.e. ($V_{sp} - V_{pi}$), was defined as the amount of deformation
15 of the formed film. Linear expansion coefficient was obtained by the following equation:

Linear expansion coefficient

$$= (V_{sp} - V_{pi}) / \text{length of specimen} / \text{temperature difference}$$

20 (2) Tensile strength

Under the conditions given in Examples and Comparative examples, a single layer was formed on each of both surfaces of the polyimide support member. This specimen in size of 5 mm × 30 mm was pulled using a tensile tester
25 (Tensilon STM-T-50BP; Tokyo Boring Co., Ltd.). The surface of the formed film was examined under microscope with magnifying factor of 200 x, and a value of load, under which cracking occurred, was defined as tensile strength.

(3) Cracking

A protective layer was formed by sputtering method. After cooling down, the surface of the specimen was examined under differential interference type microscope (XP(U)NR-A; Nikon Corporation). The specimen was examined at 30 points at random with magnifying factor of 200 x. When no cracking was found during 30 measurements, it was defined as "very good". If cracks were found at 2 points or less, it was defined as "good". If cracks were found at more than 2 points, it was regarded as "no good".

Table 1

	Primer layer	E_{UL}	S_{UL}	Seed layer	E_{SE}	S_{SE}	Expansion ratio	Strength ratio	Cracks
Example 1	CrTi ₂₀	6.9	38.4	Ta	6.5	53.0	0.13	1.38	Very good
Example 2	CrTi ₂₀	6.9	38.4	Mo	5.1	49.0	0.26	1.28	Very good
Example 3	CrTi ₂₀	6.9	38.4	Rh	8.5	54.9	0.23	1.43	Very good
Example 4	CrMo ₂₀	6.2	43.0	Ta	6.5	53.0	0.04	1.23	Very good
Example 5	CrMo ₂₀	6.2	43.0	Mo	5.1	49.0	0.18	1.13	Very good
Example 6	CrTi ₂₀	6.9	38.4	CrTi ₂₅	6.3	39.2	0.09	1.00	Good
Example 7	CrTi ₂₀	6.9	38.4	Zr	5.0	35.0	0.27	0.91	Good
Example 8	CrTi ₂₀	6.9	38.4	Nb	7.2	21.0	0.04	0.73	Good
Example 9	CrTi ₂₀	6.9	38.4	Ir	6.8	20.3	0.01	0.53	Good
Example 10	CrTi ₂₀	6.9	38.4	Mn	23.0	50.4	2.33	1.31	Good
Example 11	CrTi ₂₀	6.9	38.4	Al	23.5	4.76	2.41	0.13	Good
Example 12	CrMo ₂₀	6.2	43.0	Rh	8.5	54.9	0.37	1.27	Good
Comparative example 1	CrTi ₂₀	6.9	38.4	-	-	-	-	-	No good
Comparative example 2	CrMo ₂₀	5.8	43.0	-	-	-	-	-	No good
Comparative example 3	Cr	6.2	42.0	-	-	-	-	-	No good
Comparative example 4	Rh	8.5	54.9	-	-	-	-	-	No good

Comparative example 5	Zr	5.0	35.0	-	-	-	-	-	No good
Comparative example 6	Ta	6.5	53.0	-	-	-	-	-	No good
Comparative example 7	Mo	5.1	49.0	-	-	-	-	-	No good
Comparative example 8	Mn	23.0	50.4	-	-	-	-	-	No good
Comparative example 9	Al	23.5	4.76	-	-	-	-	-	No good
Comparative example 10	Mo	5.1	49.0	-	-	-	-	-	No good
Comparative example 11	CrTi ₂₀	6.3	39.2	-	-	-	-	-	No good

In Table 1,

E_{UL} : Linear expansion coefficient of the primer layer
(unit: 10^{-6})

5 S_{UL} : Tensile strength of the primer layer
(unit: kg/mm^2)

E_{SE} : Linear expansion coefficient of the seed layer
(unit: 10^{-6})

10 S_{SE} : Tensile strength of the seed layer
(unit: kg/mm^2)

Expansion ratio: $|E_{SE} - E_{UL}|/E_{UL}$

Strength ratio: S_{SE}/S_{UL}

As described above, a flattening layer is formed on a
15 flexible support member, and a seed layer is provided
between the above layer and a nonmagnetic primer layer
which is formed as a primer layer of the magnetic layer,
and linear expansion coefficient and tensile strength of
the seed layer and the nonmagnetic primer layer were set to
20 specific values. As a result, film strength is increased,

WHAT IS CLAIMED IS:

1. A floppy disk, comprising a primer layer, a magnetic layer, a protective layer, and a lubricating layer coated on at least one of the surfaces of a flexible nonmagnetic support member, whereby a seed layer is provided between the flexible support member and the primer layer.

2. A floppy disk according to claim 1, wherein there is provided a flattening layer, comprising a heat-resistant polymer, on the flexible nonmagnetic support member.

3. A floppy disk according to claim 1, wherein thickness of the flattening layer is within the range of 0.1 - 5 μm .

4. A floppy disk according to claim 2, wherein thickness of the flattening layer is within the range of 0.1 - 5 μm .

5. A floppy disk according to claim 1, wherein thickness of the flexible support member is within the range of 30 - 100 μm .

6. A floppy disk according to claim 2, wherein thickness of the flexible support member is within the range of 30 - 100 μm .

7. A floppy disk according to claim 3, wherein thickness of the flexible support member is within the range of 30 - 100 μm .

8. A floppy disk according to claim 4, wherein thickness of the flexible support member is within the range of 30 - 100 μm .

00670815-002700

9. A floppy disk according to claim 1, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

5 10. A floppy disk according to claim 2, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

11. A floppy disk according to claim 3, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

10 12. A floppy disk according to claim 4, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

15 13. A floppy disk according to claim 5, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

14. A floppy disk according to claim 6, wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.

20 15. A floppy disk according to claim 1, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

16. A floppy disk according to claim 2, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

25 17. A floppy disk according to claim 3, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

18. A floppy disk according to claim 4, wherein a Cr

alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

19. A floppy disk according to claim 5, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

20. A floppy disk, comprising a flattening layer with thickness of 0.1 - 5 μm , a seed layer, a nonmagnetic primer layer containing Cr alloy with Cr concentration of 77 - 100 atom %, a magnetic layer containing Co-Cr alloy with Cr concentration of 10 - 30 atom %, a protective layer, and a lubricating layer, all of said layers being coated on at least one of the surfaces of a flexible support member with thickness of 30 - 100 μm , whereby thickness of the seed layer is 5 - 100 nm, and linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$.

ABSTRACT OF THE DISCLOSURE

09576616.002700

The present invention provides a magnetic recording medium, which comprises a flattening layer with thickness of 0.1 - 5.0 μm , a seed layer, a nonmagnetic primer layer
5 containing chromium with chromium concentration of 77 - 100 atom %, a Co-Cr type alloy magnetic layer, a protective layer, and a lubricating layer coated sequentially on at least one of the surfaces of a flexible nonmagnetic support member, whereby the metal seed layer is designed in such
10 manner that linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer
15 layer satisfy the relation: $S_{SE}/S_{UL} > 1$, and a floppy disk is produced by preventing cracking during the manufacture of the floppy disk.

DECLARATION AND POWER OF ATTORNEY

SOLE/JOINT

As a below named inventor, I hereby declare that my residence, post office address and citizenship are as stated below next to my name: that I verily believe I am the original, first and sole inventor (if only one name is listed below) or a joint inventor (if plural names are listed below) of the subject matter claimed and for which a patent is sought in the application entitled:

FLOPPY DISK

which application is:

XX the attached application
(for original application)

_____ application Serial No. _____
filed _____, and amended on _____

(for declaration not accompanying application)

that I have reviewed and understand the contents of the specification of the above-identified application, including the claims, as amended by any amendment referred to above; that I acknowledge my duty to disclose information of which I am aware which is material to the patentability of this application under 37 C.F.R. 1.56, that I hereby claim foreign priority benefits under Title 35, United States Code §119, §172 or §365 of any foreign application(s) for patent or inventor's certificate listed below and have also identified on said list any foreign application for patent or inventor's certificate on this invention having a filing date before that of the application on which priority is claimed:

Application Number	Country	Filing Date	Priority Claimed
11-272644	Japan	September 27, 1999	yes

I hereby claim the benefit of Title 35, United States Code §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in a listed prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge my duty to disclose any information material to the patentability of this application under 37 C.F.R. 1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

Application Serial No.	Filing Date	Status (patented, pending, abandoned)
------------------------	-------------	--

I hereby appoint John H. Mion, Reg. No. 18,879; Donald E. Zinn, Reg. No. 19,046; Thomas J. Macpeak, Reg. No. 19,292; Robert J. Seas, Jr., Reg. No. 21,092; Darryl Mexic, Reg. No. 23,063; Robert V. Sloan, Reg. No. 22,775; Peter D. Olexy, Reg. No. 24,513; J. Frank Osha, Reg. No. 24,625; Waddell A. Biggart, Reg. No. 24,861; Robert G. McMorro, Reg. No. 19,093; Louis Gubinsky, Reg. No. 24,835; Neil B. Siegel, Reg. No. 25,200; David J. Cushing, Reg. No. 28,703; John R. Inge, Reg. No. 26,916; Joseph J. Ruch, Jr., Reg. No. 26,577; Sheldon I. Landsman, Reg. No. 25,430; Richard C. Turner, Reg. No. 29,710; Howard L. Bernstein, Reg. No. 25,665; Alan J. Kasper, Reg. No. 25,426; Kenneth J. Burchfiel, Reg. No. 31,333; Gordon Kit, Reg. No. 30,764; Susan J. Mack, Reg. No. 30,951; Frank L. Bernstein, Reg. No. 31,484; Mark Boland, Reg. No. 32,197; William H. Mandir, Reg. No. 32,156; Scott M. Daniels, Reg. No. 32,562; Brian W. Hannon, Reg. No. 32,778 and Abraham J. Rosner, Reg. No. 33,276, my attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith, and request that all correspondence about the application be addressed to **SUGHRUE, MION, ZINN, MACPEAK & SEAS**, 2100 Pennsylvania Avenue, N.W., Washington, D.C. 20037-3202.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Date September 22, 2000 First Inventor Masakazu NISHIKAWA
Residence Same as post office Signature Masakazu Nishikawa
address Post Office Address C/O FUJI PHOTO FILM CO., LTD., 12-1,
Citizenship JAPAN Ohgicho 2-chome, Odawara-shi, KANAGAWA 250-0001
JAPAN

Date September 22, 2000 Second Inventor Makoto NAGAO
Residence Same as post office Signature Makoto Nagao
address Post Office Address C/O FUJI PHOTO FILM CO., LTD., 12-1,
Citizenship JAPAN Ohgicho 2-chome, Odawara-shi, KANAGAWA 250-0001
JAPAN